

# Material Data Sheet

## VeroClear RGD810

	ASTM	Units	Metric	Units	Imperial
Tensile Strength	D-638-03	MPa	50-65	psi	7250-9450
Elongation of break	D-638-05	%	10-25	%	10-25
Modulus of Elasticity	D-638-04	MPa	2000-3000	psi	290,000-435,000
Flexural Strength	D-790-03	MPa	75-110	psi	11000-16000
Flexural Modulus	D-790-04	MPa	2200-3200	psi	320,000-465,000
HDT, °C @ 0.45MPa	D-648-06	°C	45-50	°F	113-122
HDT, °C @ 1.82MPa	D-648-07	°C	45-50	°F	113-122
Izod Notched Impact	D-256-06	J/m	20-30	ft lb/inch	0.375-0.562
Water Absorption	D-570-98 24hr	%	1.1-1.5	%	1.1-1.5
Tg	DMA, E>>	°C	52-54	°F	126-129
Shore Hardness (D)	Scale D	Scale D	83-86	Scale D	83-86
Rockwell Hardness	Scale M	Scale M	73-76	Scale M	73-76
Polymerized Density	ASTM D792	g/cm <sup>3</sup>	1.18-1.19		
Ash content	USP281	%	0.02-0.06	%	0.02-0.06